



## FAIRSKY INDUSTRIAL CO., LIMITED

Tel: +86-312-6793216, +86-312-6793218

Fax: +86-312-3110089

Email: [fairskychem@yahoo.com.cn](mailto:fairskychem@yahoo.com.cn)

[fairsky.chem@yahoo.com.cn](mailto:fairsky.chem@yahoo.com.cn)

URL: <http://www.fairskyindustrial.com>

Add: Room2901, Parkway Court  
No.9, SwanRoad 98#, Baoding City Hebei  
China 071000

---

### Nickel Sulphamate Solution

**Formula:**  $\text{Ni}(\text{NH}_2\text{SO}_3)_2 \cdot x\text{H}_2\text{O}$

**CAS No.:** 13770-89-3

**M.W.:**

**Properties:** Offering fast settling speed and good dispersion and low plating stress, its current efficiency is 99% at least

#### Specification (%):

Ni	11.0%min
Fe	5 ppm max
Zn	2 ppm max
Cu	2 ppm max
Pb	1 ppm max
Mn	2 ppm max
Ca	10 ppm max
Mg	10 ppm max
Water insoluble	0.01%max

**Application:** electrical industry, casting, nickel plating, gild, coinage, micro-groove record, Ni/Cd battery

**Storage:** Store in a cool, ventilating place. Prevent package from breaking and deliquescing.

**Packing:** 25L PE drums.